


# Montreux

Porcelain Tile



AUGUST 6 2025



 Stocked In The USA  
2-3 week lead time

1 Color | 3 Formats | 1 Finish

## Details

## Stocked Color 12" x 24"

### Size




12" x 24"

### Additional Sizes



(2" x 2") 12" x 12" Mosaic



3" x 12" Skirting

3/8" Thickness  
EDGE: Pressed

### Installation Recommendations:

- For 12" x 24" pressed tiles: 1/8" grout joint and 33% offset pattern recommended.
- We recommend choosing a grout color that closely matches the tile.



Montreux  
Matte

## Symbols



Floor & Wall



Residential



Commercial



Multi-Family



Matte



Glazed Porcelain



Pressed



Shade Variation

## Packing

## Pcs/Box

## SF/Box

## Lbs/Box

12" x 24"  
(2" x 2") 12" x 12" Mosaic  
3" x 12"

8pcs  
5pcs  
10pcs

15.06 SF  
4.74 SF  
2.37 SF

60.58 Lbs  
20.5 Lbs  
11.6 Lbs

# Montreux (continued)



AUGUST 6 2025

## TECHNICAL INFORMATION

<i>Technical Characteristics</i>	<i>ISO</i>	<i>Unit</i>	<i>Results</i>
Dim. var. in rel. w. of the greater side	10545-2	%	+/-0.60
Dim. var. in rel. w. of the minor side	10545-2	%	+/-0.60
Dim. var. in rel. average of the greater side	10545-2	%	+/-0.25
Dim. var. in rel. average of the minor side	10545-2	%	+/-0.25
Thickness variation	10545-2	%	+/-5.0
Straightness of the greater side	10545-2	%	+0.15/-0.20
Straightness of the minor side	10545-2	%	+0.15/-0.20
Deviation from orthogonality of the greater side	10545-2	%	+/-0.4
Deviation from orthogonality of the minor side	10545-2	%	+/-0.4
Central diagonal curvature deviation	10545-2	%	+0.3/-0.1
Deviation of the curvature of the sides	10545-2	%	+0.3/-0.1
Deviation of the curvature of the sides	10545-2	%	+0.3/-0.1
Bending over diagonal	10545-2	%	+/-0.30
Quality of surface	10545-2	%	>=95
Water absorption	10545-3	%	<=0.5
Resistance to bending	10545-4	N/mm <sup>2</sup>	>=35
Breaking strength	10545-4	N	>=1500
Class of usage		Use	5
Thermal shock resistance	10545-9	-	
Linear expansion coefficient x 10 <sup>-6</sup>	10545-8	C-1	6.3 a 7.0
Moisture expansion	10545-10	mm/m	<=0.30
Grazing resistance	10545-11	-	OK
Resistance to chemicals	10545-13	-	GA
Resistance attacks acid/alkaline	10545-13	-	GLB
Surface resistance to stains	10545-14	-	Min.Class 4
Coefficient of friction wet	NBR13818		>=0.4
Coefficient wet	ASTM1028	-	
Changes in hue			V3

Note: Product in accordance with the standard of ABNT NBR 15463  
Reaction to fire evaluation (NBR15575): Class I (non-combustible)