

Cerato

Glazed Porcelain Tile



 Stocked In The USA
2-3 week lead time

4 Colors | 4 Formats | 1 Finish

Featured: Cerato I Platinum

Details


Sizes



12" x 24"
Matte
Pressed



13" x 13"
Matte
Pressed



20" x 20"
Matte
Pressed

Additional Format



(2" x 2") 12" x 12" Mosaic
Matte

5/16" Thickness

Installation Recommendation:

Choose a grout color that closely matches the tile.

Colors



Pearl



Desert



Platinum



Graphite

Symbols



Floor & Wall



Residential



Commercial



Multi-Family



Matte



Glazed Porcelain



Pressed



Shade Variation

Packing

Pcs/Box

SF/Box

Lbs/Box

12" x 24"
13" x 13"
20" x 20"
(2" x 2") 12" x 12" Mosaic Sheet

8pcs
11pcs
6pcs
10pcs

15.5 SF
12.92 SF
15.93 SF
9.58 SF

59.45 Lbs
44.97 Lbs
63.55 Lbs
38.44 Lbs

TECHNICAL INFORMATION

Water Absorption	ANSI / ISO - (%)	<0.5%
Abrasion Resistance	ANSI / ISO	Class 4
Scratch Hardness	ANSI / ISO - (Mohs)	Matte 8
Breaking Strength	ANSI - (lbf) ISO - (N)	> 350 > 1600
Shade Variation		V3
Slip Resistance	ANSI - DCOF (WET) ISO - R VALUE	Matte ≥ 0.60 (ID, IW, IW+, EW*, O/G*) Matte R10
Chemical Resistance	ANSI / ISO	Class A
Stain Resistance	ANSI ISO	Class A Class 5
Frost Resistance	ANSI / ISO	Pass

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

USAGE RECOMMENDATIONS

<i>Application</i>		<i>Wall</i>	<i>Floor</i>
Interior	Residential	●	ID, IW, IW+, EW*, O/G*
	Commerical	●	ID, IW, IW+, EW*, O/G*
	Heavy Commercial	●	
Exterior	Residential / Commercial	●	ID, IW, IW+, EW*, O/G*

These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases

* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3