

Radiance

Glazed Porcelain Tile



Stocked In The USA
2-3 week lead time

8 Colors | 4 Formats | 2 Finishes

Featured: Radiance | Grigio

Details

Sizes



12" x 24"
Heritage Texture / Matte



13" x 13"
Matte



20" x 20"
Matte

Additional Size



(2" x 2") 12" x 12" Mosaic
Matte

5/16" Thickness
EDGE: Pressed

Installation Recommendations:

- For 12" x 24" pressed tiles: 1/8" grout joint and 33% offset pattern recommended.
- We recommend choosing a grout color that closely matches the tile.

Colors



Bianco



Statuario




Onyx



Calacatta



Ivory



Dune



Grigio



Carbon

Symbols



Floor & Wall



Residential



Commercial



Multi-Family



Matte



Glazed Porcelain



Pressed



Shade Variation

Packing

12" x 24"
13" x 13"
20" x 20"
(2" x 2") 12" x 12" Mosaic

Pcs/Box

8pcs
11pcs
6pcs
10pcs

SF/Box

15.5 SF
12.92 SF
15.93 SF
9.58 SF

Lbs/Box

59.45 Lbs
44.97 Lbs
63.55 Lbs
38.45 Lbs

Radiance (continued)



TECHNICAL INFORMATION

Water Absorption	ANSI / ISO - (%)	<0.5%
Abrasion Resistance	ANSI / ISO	Class 4
Scratch Hardness	ANSI / ISO - (Mohs)	Matte 8
Breaking Strength	ANSI - (lbf) ISO - (N)	> 350 > 1600
Shade Variation		V3
Slip Resistance	ANSI - DCOF (WET) ISO - R VALUE	≥0.60 (ID, IW, IW+, EW*, O/G* Matte R10)
Chemical Resistance	ANSI / ISO	Class A
Stain Resistance	ANSI ISO	Class A Class 5
Frost Resistance	ANSI / ISO	Pass

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

USAGE RECOMMENDATIONS

<i>Application</i>		<i>Wall</i>	<i>Floor</i>
Interior	Residential	●	ID, IW, IW+, EW*, O/G*
	Commerical	●	ID, IW, IW+, EW*, O/G*
	Heavy Commercial	●	
Exterior	Residential / Commercial	●	ID, IW, IW+, EW*, O/G*

These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases

* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3