

# Sint

Glazed Porcelain Tile



Featured: Sint | Dawn

4 Colors | 3 Formats | 1 Finish

### Details

#### Sizes



12" x 24"  
Matte  
Pressed



13" x 13"  
Matte  
Pressed

#### Additional Format




(2" x 2") 12" x 12" Mosaic  
Matte


5/16" Thickness

**Installation Recommendation:**  
Choose a grout color that closely  
matches the tile.


### Colors




Dawn



Fog



Sienna



Umber

### Symbols



Floor & Wall



Residential



Commercial



Multi-Family



Matte



Glazed Porcelain



Pressed



Shade Variation

### Packing

### Pcs/Box

### SF/Box

### Lbs/Box

12" x 24"  
13" x 13"  
(2" x 2") 12" x 12" Mosaic Sheet

8pcs  
11pcs  
10pcs

15.5 SF  
12.92 SF  
9.58 SF

59.45 Lbs  
44.97 Lbs  
38.44 Lbs

## TECHNICAL INFORMATION

Water Absorption	ANSI / ISO - (%)	<0.5%
Abrasion Resistance	ANSI / ISO	Class 4
Scratch Hardness	ANSI / ISO - (Mohs)	8
Breaking Strength	ANSI - (lbf) ISO - (N)	> 350 > 1600
Shade Variation		V3
Slip Resistance	ANSI - DCOF (WET) ISO - R VALUE	Matte $\geq 0.60$ (ID, IW, IW+, EW*, O/G*) Matte R10
Chemical Resistance	ANSI / ISO	Class A
Stain Resistance	ANSI ISO	Class A Class 5
Frost Resistance	ANSI / ISO	Pass

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

## USAGE RECOMMENDATIONS

<i>Application</i>		<i>Wall</i>	<i>Floor</i>
Interior	Residential	●	ID, IW, IW+, EW*, O/G*
	Commerical	●	ID, IW, IW+, EW*, O/G*
	Heavy Commercial	●	
Exterior	Residential / Commercial	●	ID, IW, IW+, EW*, O/G*

These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases

\* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3